

**TEST REPORT**

REPORT NO.KP/2009/60162A-01

DATE: 2009/6/19

PAGE: 1 OF 2



The following sample(s) was/were submitted and identified by/on behalf of the client as :

**CLIENT** : WangTech Enterprise Co.,Ltd.  
**SAMPLE DESCRIPTION** : Super Diesel with "Full-Burn Nano Fuel Economizer".  
**SAMPLING DATE** : 2009/06/10.  
**TESTING DATE** : 2009/06/12 TO 2009/6/19 .  
**SAMPLE RECEIVED** : 2009/06/12.  
**SAMPLE SUBMITTED BY** : WangTech Enterprise Co.,Ltd.


WE HAVE TESTED THE SAMPLE(S) SUBMITTED AS REQUESTED AND THE FOLLOWING RESULTS WERE OBTAINED.

| TEST ITEM(S)                                  | UNIT               | METHOD     | SPEC |      | RESULT |
|---|--------------------|------------|------|------|--------|
|   |                    |            | MIN  | MAX  |        |
| Cetane Index                                  | ---                | ASTM D976  | 48   | ---  | 52     |
| Density,15°C                                  | g/mL               | ASTM D4052 | ---  | ---  | 0.8443 |
| Polyaromatic hydrocarbons(POLY-AH)            | wt%                | ASTM D6591 | ---  | 11   | 4.79   |
| Sulfur(S)                                     | ppm                | ASTM D5453 | ---  | 50   | 25     |
| Flash Point                                   | °C                 | ASTM D93   | 52   | ---  | 73.5   |
| Micro Carbon Residue,10% distillation residue | wt%                | ASTM D4530 | ---  | 0.3  | <0.1   |
| Ash   | wt%                | ASTM D482  | ---  | 0.01 | <0.001 |
| Water & Sediment                              | Vol%               | ASTM D2709 | ---  | ---  | 0      |
| Copper Corrosion Strip at 50°C,3hrs           | ---                | ASTM D130  | ---  | NO.1 | 1b     |
| Viscosity,40°C                                | mm <sup>2</sup> /s | ASTM D445  | 2.0  | 4.5  | 3.369  |
| Distillation Range                            | ---                | ---        | ---  | ---  | ---    |
| 90%   | °C                 | ASTM D86   | ---  | ---  | 335.6  |
| 95%   | °C                 | ASTM D86   | ---  | 360  | 349.2  |
| Pour Point                                    | °C                 | ASTM D5950 | ---  | -3   | -6     |

NOTE 1 : 1b = Slight tarnish; dark orange.

NOTE 2 : All test results are conform with specification for super diesel by CPC.

<END>



**Liwen Liu / Asst.Manager**  
**Signed for and on behalf of**  
**SGS Taiwan Limited**

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部分複製。  
 This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at [www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm) and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at [www.sgs.com/terms\\_e-document.htm](http://www.sgs.com/terms_e-document.htm). Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

## TEST REPORT

REPORT NO.KP/2009/60162A-01

DATE: 2009/6/19

PAGE: 2 OF 2

## SAMPLE PHOTO



<END>

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部分複製。  
This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at [www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm) and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at [www.sgs.com/terms\\_e-document.htm](http://www.sgs.com/terms_e-document.htm). Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.